

HF-55

SEAMLESS COPPER-COATED CORED WIRES FOR MILD STEELS



AWS A5.29 E81T1-Ni1C-J

EN ISO 17632-A : T 46 6 1Ni P C1 1 H5

APPROVALS: CCS

FEATURES:

- Extremely low diffusible hydrogen weld deposit
- Easy slag removal
- Excellent current transfer
- Very good feeding performance
- Good CVN impact toughness down to -60 °C
- Excellent weldability and high productivity

APPLICATIONS

- Steel structures
- Offshore
- Pipelines
- Vessels
- General fabrication
- Heavy equipment

WIRE TYPE	Gas shielded rutile flux-cored wire with rapidly solidifying slag
SHIELDING GAS	100% CO ₂ , Gas flow 15-25 l/min
POLARITY	DC+
WELDING POSITIONS	All Position
TYPICAL DIFFUSIBLE HYDROGEN	<3.0 ml / 100g; Guaranteed for the total processing time < 4.0 ml / 100 g
STANDARD DIAMETERS	1.2mm
RE-DRYING	Not required due to seamless wire design
STORAGE	Stored in a dry, enclosed environment, in its original undamaged packaging
PACKAGING	5kg Plastic spool, 15kg Plastic spool, 200kg Drum

DEPOSITED METAL ANALYSIS (WT%, TYPICAL)

Carbon (C)	0.030	Chromium (Cr)	0.020	Phosphorus (P)	0.009
Silicon (Si)	0.400	Nickel (Ni)	0.950	Sulphur (S)	0.004
Manganese (Mn)	1.100	Molybdenum (Mo)	0.010		

MECHANICAL PROPERTY

Yield Strength (Mpa)	Tensile Strength (MPa)	Elongation (%)	Charpy V J/°C
530(≥470)	590(550-690)	25(≥19)	72 I-60 (≥27)

TYPICAL OPERATING PROCEDURE

Diameter (mm)	Volt (V)	Ampere (A)	Electrode Stick-out (mm)	Gas Flow (L/min)
1.2	22-32	180-300	15-20	15-25

XinXiang HeGuang Technology Co., Ltd.