

HG-81K2

SEAMLESS COPPER-COATED CORED WIRES FOR MILD STEELS



AWS A5.29 E81T1-K2C-J H4

EN ISO 17632-A : T 46 6 1.5Ni P C1 1 H5

APPROVALS: /

FEATURES:

- . Extremely low diffusible hydrogen weld deposit
- . Easy slag removal
- . Excellent current transfer
- . Very good feeding performance
- . Good CVN impact toughness down to -60 °C
- . Excellent weldability and high productivity

APPLICATIONS

- . Steel structures
- . Offshore
- . Pipelines
- . Vessels
- . General fabrication
- . Heavy equipment

WIRE TYPE

Gas shielded rutile flux-cored wire with rapidly solidifying slag

SHIELDING GAS

100% CO₂, Gas flow 15-25 l/min

POLARITY

DC+

WELDING POSITIONS

All Position

TYPICAL DIFFUSIBLE HYDROGEN

<3.0 ml / 100g; Guaranteed for the total processing time < 4.0 ml / 100 g

STANDARD DIAMETERS

1.2mm

RE-DRYING

Not required due to seamless wire design

STORAGE

Stored in a dry, enclosed environment, in its original undamaged packaging

PACKAGING

5kg Plastic spool, 15kg Plastic spool, 200kg Drum

DEPOSITED METAL ANALYSIS (WT%, TYPICAL)

Carbon (C)	0.032	Chromium (Cr)	0.033	Phosphorus (P)	0.013
Silicon (Si)	0.297	Nickel (Ni)	1.604	Sulphur (S)	0.005
Manganese (Mn)	0.995	Molybdenum (Mo)	0.009		

MECHANICAL PROPERTY

Yield Strength (Mpa)	Tensile Strength (MPa)	Elongation (%)	Charpy V J/°C
495(≥470)	580(550-690)	25(≥19)	60 /-60 (≥27)

TYPICAL OPERATING PROCEDURE

Diameter (mm)	Volt (V)	Ampere (A)	Electrode Stick-out (mm)	Gas Flow (L/min)
1.2	22-32	180-300	15-20	15-25

XinXiang HeGuang Technology Co., Ltd.